

SoFT TOUcH® White

The original SoFT TOUcH® with white finished and printable



DERPROSA™
PREMIUM LUXURY FILMS



www.derprosa.com

MAIN SPECIFICATIONS / CARACTERÍSTICAS

EN Highly opaque SoFT TOUcH® matte film with optimum whiteness • Printable by Offset (using oxidative inks, specific for non-porous material) and screen printing • It's compatible with any kind of UV inks, spot UV and hot stamping.

ES Film mate SoFT TOUcH®, altamente opaco, con una blancura óptima • Imprimible por offset (utilizando tintas oxidativas, específicas para materiales no porosos) • Es compatible con cualquier tipo de tintas UV, barnices UV y hot stamping.

TECHNICAL SPECIFICATIONS / ESPECIFICACIONES TÉCNICAS

PROPERTIES PROPIEDADES	SoFT TOUcH® WET THERMAL		UNITS UNIDADES	TEST METH MET. ENSAYO
	37W241			
Thickness Espesor	37		µm	-
	1,5		Mills	
Yield Rendimiento	27,4		m²/kg	Internal Method Método Interno
	19,273		ln²/Lb	
Light tansmission Transferencia de la luz	≤ 20		%	ASTM 1003
Whiteness Blancura	≥ 90		%	ASTM - E313
Gloss Brillo	≤ 9		%	ASTM D 2457 45°
Dyne level Tensión superficial	≥ 40		mN/m	ASTM D 2578
Dynamic C.O.F. C.O.F. Dinámico	0,70		-	ASTM D 1894
Application temperature Temperatura de aplicación	95-115		°C	Internal Method Método Interno
	200-240		°F	
Lamination strength Fuerza de laminación	≥7,5		N/25,4mm	Internal Method Método Interno
	≥1,68		Lb/Inch	

The above information is based on conclusive test evidence and TAGHLEEF INDUSTRIES S.L.U. experience. The Co. refuses any responsibility arising from the use, handling or treatment of products after delivery and its guarantee is only related to the quality of the products, as specified on the transaction contract. The delivered raw and packaging materials have been manufactured following the current laws and any important change in the properties of them, will be notified previously in order to be accepted by the customer.

La información reseñada está basada en pruebas contrastadas y la experiencia de TAGHLEEF INDUSTRIES S.L.U. La Cía. no se responsabiliza del uso, manipulación o tratamiento a que sean sometidos sus productos posteriormente a su suministro, y sólo garantiza exclusivamente la calidad de los mismos, según se indica en el contrato de compraventa. La materia prima y embalajes suministrados se han elaborado según ley vigente y son aptos para su uso previsto. Los cambios significativos en las propiedades del producto debido a modificaciones en la fabricación de aquellos, se comunicarán al cliente con antelación para su aceptación.



www.derprosa.com
www.ti-films.com



DERPROSA™
PREMIUM LUXURY FILMS



Taghleef Industries