



Mulch Films

Standard black

Property	Units	Target
Gauge	Mils	1.00
Emboss thickness	Mils	1.8
Dart drop	Grams	500
MD Ultimate Tensile	Grams/In	2212
TD Ultimate Tensile	Grams/In	180
MD Elongation Tensile	%	547
TD Elongation Tensile	%	629
MD Tensile @ 25%	Grams/IN	470
TD Tensile @ 25%	Grams/In	414
MD Trouser Tear	Grams/In	>35

THIS IS NOT A SPECIFICATION. THE ABOVE INFORMATION REPRESENTS TYPICAL PHYSICAL PROPERTY DATA ONLY.

Berry Global Inc., offers this information with no obligation or liability for products made with this film. The film product described above

is sold without warranty, express or implied. Also, this film product does not infringe the claims of any current U.S. Patent and nothing

herein shall be construed as a recommendation or suggestion in conflict with existing patents covering film applications.