



Mulch Films

Standard black/white

Property	Units	Target
Gauge	Mils	1.25
Emboss thickness	Mils	2.0
Reflectance	%	53.0
Dart (green)	Grams	425
MD Ultimate Tensile	Grams/In	2104
TD Ultimate Tensile	Grams/In	1898
MD Elongation Tensile	%	480
TD Elongation Tensile	%	537
MD Tensile @ 25%	Grams/IN	591
TD Tensile @ 25%	Grams/In	522
MD Trouser Tear	Grams/In	>35

THIS IS NOT A SPECIFICATION. THE ABOVE INFORMATION REPRESENTS TYPICAL PHYSICAL PROPERTY DATA ONLY.

Berry Global Inc., offers this information with no obligation or liability for products made with this film. The film product described above

is sold without warranty, express or implied. Also, this film product does not infringe the claims of any current U.S. Patent and nothing

herein shall be construed as a recommendation or suggestion in conflict with existing patents covering film applications.