



Mulch Films

Standard black/white

Property	Units	Target
Gauge	Mils	1.10
Emboss thickness	Mils	2.2
Reflectance	%	52
Dart Drop	Grams	455
MD Ultimate Tensile	Grams/In	1885
TD Ultimate Tensile	Grams/In	1649
MD Elongation Tensile	%	465
TD Elongation Tensile	%	566
MD Tensile @ 25%	Grams/IN	516
TD Tensile @ 25%	Grams/In	407
MD Trouser Tear	Grams/In	>35

THIS IS NOT A SPECIFICATION. THE ABOVE INFORMATION REPRESENTS TYPICAL PHYSICAL PROPERTY DATA ONLY.

Berry Global Inc., offers this information with no obligation or liability for products made with this film. The film product described above

is sold without warranty, express or implied. Also, this film product does not infringe the claims of any current U.S. Patent and nothing

herein shall be construed as a recommendation or suggestion in conflict with existing patents covering film applications.